



## Liquid Silk Matt Gold for bone china and porcelain MG 1316-16% H

### 1 General Information

MG 1316-16% H is medium viscos liquid silk matt gold developed for the decoration of bone china. It can also be used for the decoration of porcelain and earthenware items. After firing the material shows a yellow red gold colour shade.

Fired decoration showed in tests a very good detergent and ASTM resistance. With these characteristics MG 1316-16% H is typically used for higher quality dinnerware and institutional tableware.

MG 1316-16% H is also suitable to be used in our Two-Fire-Etching-Imitation-System.

### 2 Standard Firing Range

| Substrate  | Firing range |
|------------|--------------|
| Porcelain  | 780 – 880°C  |
| Bone China | 750 – 880°C  |

The firing result depends on the firing temperature, the total cycle time, the soak time as well as of the glaze chemistry of the substrate decorated. To achieve an optimal firing result, we recommend firing tests under the users own individual conditions.

### 3 Properties of the preparations

The major characteristics of a Heraeus precious metal preparation are determined by its production recipe. From each lot produced, we take a sample and check defined characteristics.

In case of liquid silk matt gold's we check the viscosity and the application properties comparing them with the defined standard. After the firing, we check the optical appearance – glossiness and gold colour shade. Controlling each single production lot assures the highest product quality and lot-to-lot stability.

#### 3.1 Processing

We deliver MG 1316-16% H H ready to use. The material can be applied without further thinning and distinguish themselves by its excellent application properties and a sharp outline.

#### 3.2 Storage

Silk matt golds are subject to an ageing process. The viscosity increases during storage. Besides the materials contain a matting agent which tends to settle. Therefore prior to the usage the material needs to be shaken.

We recommend the storage of silk matt materials at room temperature (20°C) and the usage of the materials within six months time.

#### 3.3 Consumption

The material consumption depends on the thickness of the applied precious metal layer. Under our conditions, the consumption is approx. 0,15 to 0,30g/100 cm<sup>2</sup>.

## 4 Properties of finished decorations

The main properties of fired bright precious metal decorations comprise brilliance and precious metal tone, dishwasher resistance and resistance to mechanical and chemical attack.

These properties are influenced by a number of factors. The high quality of the preparation used is an absolute prerequisite for manufacturing high-quality decorations. The quality of a fired decoration, however, derives from the interplay of preparation, application, substrate surface and firing conditions. A variation in only one factor – for instance, the firing conditions, has an immediate influence that leads to altered properties of the fired decoration.

We have processed the bright precious metal preparations under defined conditions. Then we determined the properties of the finished decorations. The following data indicate achievable quality features for the finished decorations manufactured with bright precious metal preparations. They must, however, always be checked by the user under his own individual conditions.

### 4.1 Dishwasher resistance

All details as to whether decorations are dishwasher durable are to be regarded as approximate values, as test results vary widely according to the type of dishwasher, washing programme, washing-up detergent, water quality and firing conditions.

Heraeus tests whether finished decorations are dishwasher durable, roughly following the test-washing programme of the Technical Standards Committee for Material Testing (Fachnormenausschuss Materialprüfung) in a Miele continuous dishwasher. If a decoration withstands 500 washing cycles essentially without damage, we designate it as dishwasher durable. If it withstands 1000 washing cycles, we designate it as dishwasher resistant.

Test decorations prepared with MG 1316-16% H showed a very good detergent resistance.

### 4.2 Abrasion resistance

Gold decorations with MG 1316-16% H showed a reasonable scratch resistance.

### 4.3 Oxidation resistance

MG 1316-16% H does not contain silver and therefore fired decorations do not bare the risk of oxidation.

## 5 Application recommendations

### 5.1 Preparation for the decoration

Work in a well-ventilated room. Good printing conditions occur at a room temperature of 20 to 25°C.

Make sure that the surface of the object to be decorated is clean and dry. Dust, fingerprints and water condensation can affect the decoration while firing.

Take care that the object to be decorated is not taken from a cold store into a warm shop. A fine condensation film may occur, which is not visible for the naked eye. Result: Firing disturbance (pinholes) in the fired precious metal decoration! Allow enough time for the substrate to adjust to the decoration room temperature.

### 5.2 Application of the material

Please shake the material intensily before usage, so that probably settled down matting agent is getting again homogeneously distributed within liquid material.

Draw from the bottle only as much as you can consume within 15 or 30 minutes and close the bottle. Consider that the solvent continuously evaporates in air and therefore the viscosity slowly increases.

Apply the preparation in a moderate layer thickness onto the object to be decorated. A too thin layer influences the mechanical, chemical and optical properties of the fired decoration. In extreme cases, it can lead to a reddish colour of the surface without any gold character. A too thick layer may lead to cracking, blistering, or to a matt surface.

In case the preparation is used for spraying, thinning with about 30% thinner V 35, V 16 or V 18 is required. Ensure a dust free environment during the application as well as during the time to drying. A wet surface is attractive to dust. After drying fire the item as soon as possible.

### 5.3 Firing

During the first heating phase the organic components of the preparation burn off. This process is completed at approx. 400°C. The gold film is formed. A constant, slow temperature increase, enough oxygen and sufficient ventilation are decisive for the quality of the fired precious metal decoration.

The firing profile considerably influences the mechanical and chemical properties of the fired decoration.

The rate of cooling has no major influence on the quality of the gold decoration, unlike the firing temperature and soak time. However, the firing process should not be stopped too abruptly after the soak time. If the rate of cooling is too fast, there may be a danger of damaging the article.

## 6.0 Typical defects, root causes and countermeasures

| Defect   | Possible Cause  | Counter measure  |
|--|---|--|
| blurred contours, running precious metal                   | too much thinning of the product  | leave the bottle open for a while, so that some of the solvent can evaporate   |
|  | the thinner was too fat or drying too slowly  | leave the bottle open for a while, so that some of the solvent can evaporate   |
|  | too much organic fumes in the furnace   | reduce the number of objects in the furnace  |
| The fired precious metal decoration is too glossy.         | the liquid silk matt material had not been shaken prior to usage respectively not been shaken intense enough to distribute settled matting agent homogeneously within the material.   | Shake the silk matt material longer before the usage.  |
|  | The deposit of the material is too thin.  | Increase the material deposit layed down by brush.   |
| The fired precious metal decoration looks to matt / dull.  | Possibly a too thick deposit of material has been applied.  | Reduce the material deposit.   |
|  | The material has thickened up during storage / lost solvent.  | Substitute the lost solvent with thinner and shake the material intently before usage to assure a homogeneous distribution of the matting agent within the material.                         |
| preparation shows bad application                          | viscosity is too high after long application or long storage  | thinning of the product with V 35, V 16 or V 18  |
| spots, firing disturbance                                  | contamination as dust, fingerprints or water condensation   | Carefully clean the object before decorating   |
|  | problems in the kiln such as: <ul style="list-style-type: none"> <li>reduced atmosphere in kiln</li> <li>insufficient ventilation</li> <li>heat increase is too fast during critical phase between 200-400°C</li> <li>too many objects in the kiln</li> </ul> | <ul style="list-style-type: none"> <li>increase air addition</li> <li>improve ventilation</li> <li>reduce the heating speed</li> <li>reduce the number of the objects in the kiln</li> </ul> |
| Precious metal chips offs during firing                    | contamination of the surface causes chip off  | clean the substrate before decorating  |
|  | the layer of the product it too thick   | reduce layer of the product  |
| low mechanical resistance of the precious metal decoration | firing temperature is too low   | increase firing temperature  |
|  | layer of the product is too thin  | increase layer thickness   |
| fine pinholes  | pinholes can be released by moisture on the surface of the decorated object. Taking objects from a cool store into a warm shop leads to invisible condensation on the surface.  | allow enough time for the ware to reach shop temperature, so that the condensation has time to evaporate.  |